

Subject:	Clarification of cross-cut incision
Proposal:	ADAL's request dated 24 April 2017
QUALICOAT resolution:	<p><u>Resolution No. 22/TC 23.05.17</u></p> <p>The TC agreed with ADAL's proposal that the term "cross-cut" should be replaced by two references "cross-hatch" and "cross-cut" in the relevant parts of the Specifications.</p>
Date of ratification:	22–23 November 2017
Date of application:	1 January 2018
Amendment to the Specifications:	Word "cross-cut" replaced by "cross-hatch" in section 2.4.2
<p>2.4.2 Wet adhesion</p> <p>Boiling water</p> <p>Immerse a sample in boiling demineralised water using method 1 or 2 as described in § 2.16. Remove the sample and allow it to cool down to room temperature. Carry out the test as detailed in § 2.4.1. The <u>cross-hatch</u> shall be made after one hour but within two hours.</p> <p>[...]</p>	